



Smith's Quay, Hazel Road  
 Woolston, Southampton  
 SO19 7GB, Great Britain  
 Telephone: (+44) 02380 434646  
 Email: info@bridgerubber.co.uk  
 Website: www.bridgerubber.com



## Red Natural Rubber 38 ShA Abrasion Resistant Data Sheet

<b>PROPERTIES</b>	<b>METRIC VALUE</b>
Specific Gravity	1.05 ± 0.05
Hardness	38 ± 5 ShA
Tensile Strength (min)	190kg / cm <sup>2</sup>
Elongation at Break (min)	500%
Compression Set (70°C / 24 hrs / 25% set) (max)	30%
Tear Resistance (angular) min	45kg / cm <sup>2</sup>
Abrasion Resistance (max)	88 mm <sup>3</sup>
<b>PROPERTIES - HEAT AGING (72 hrs at 70°C)</b>	<b>METRIC VALUE</b>
Hardness (pts)	+5 (max)
Tear Strength (%)	+10 / -15
Elongation at Break (%)	+10 / -25
IRM Oil No.1	Not Recommended
IRM Oil No.2	Not Recommended
IRM Oil No.3	Not Recommended
<b>CHEMICAL RESISTANCE</b>	
Ozone	Fair
Dilute Acids and Bases	Not Recommended
Concentrated Acids and Bases	Not Recommended
Oils	Not Recommended
Solvents	Not Recommended
Temperature Range	-40°C - 80°C
Colour	Red