



Smith's Quay, Hazel Road  
 Woolston, Southampton  
 SO19 7GB, Great Britain  
 Telephone: (+44) 02380 434646  
 Email: info@bridgerubber.co.uk  
 Website: www.bridgerubber.com



## Viton 70 ShA Commercial Grade Data Sheet

<b>PROPERTIES</b>	<b>METRIC VALUE</b>
Specific Gravity	1.98 ± 0.05
Hardness	70 ± 5 ShA
Tensile Strength (min)	10kg / cm <sup>2</sup>
Elongation at Break (min)	200%
Compression Set (70°C / 22 hrs / 25% set) (max)	50%
Temperature Range	-30°C - 210°C
Polymer (FKM)	66% Flourine
Colour	Black
<b>CHEMICAL RESISTANCE</b>	
Ozone	Excellent
Dilute Acids and Bases	Excellent
Concentrated Acids and Bases	Excellent
Oils	Good
Solvents	Good